



# Standard Specification for Tungsten Base, High-Density Metal<sup>1</sup>

This standard is issued under the fixed designation B 777; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers the requirements for four classes of machinable, high-density tungsten base metal produced by consolidating metal powder mixtures, the composition of which is mainly tungsten. This material specification may be used for bare parts or for parts that may be coated with other materials for protection against corrosion and abrasion.

1.2 *Intended Use*—Parts made from this material are intended for uses such as weights or counter-balances in static or dynamic balancing, high-speed rotating inertia members, radiation shielding, hypervelocity impact, and vibration-damping applications.

1.3 *Special Applications*—For particular applications, properties or requirements other than those specified in Sections 5, 6, and 7 of this specification may be important. These alloys may contain elements which make them magnetic. Where freedom from magnetic response is required, this should be specified in the purchase order. Class 4 is not available in a non-magnetic grade. For purposes of this specification, non-magnetic material is defined as material having a maximum magnetic permeability of 1.05 (see Test Method B 193). Also for special applications involving large sections, methods for determining internal quality, such as mechanical tests on specimens from these larger sections or suitable nondestructive tests may be applied. If required, these additional tests shall be specified in the purchase order.

1.4 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

A 600 Specification for Tool Steel High Speed

B 193 Test Method for Resistivity of Electrical Conductor Materials

B 311 Test Method for Density Determination for Powder Metallurgy (P/M) Materials Containing Less Than Two Percent Porosity

D 3951 Practice for Commercial Packaging

E 3 Guide for Preparation of Metallographic Specimens

E 8 Test Methods for Tension Testing of Metallic Materials

E 18 Test Methods for Rockwell Hardness of Metallic Materials

E 407 Practice for Microetching Metals and Alloys

2.2 *Federal Standard:*

Fed. Std. No. 151 Metals, Test Methods<sup>3</sup>

## 3. Classification

3.1 The tungsten base metal shall be of the following classes (see Table 1 and Table 2), as specified (see 4.1):

Class	Tungsten, Nominal Wt. %
1	90
2	92.5
3	95
4	97

## 4. Ordering Information

4.1 Orders for tungsten base, high-density metal should specify the following:

4.1.1 Title, designation, and year of issue of this specification,

4.1.2 Class, (see 3.1),

4.1.3 Machinability requirements, if any (see 7.3),

4.1.4 Quantity,

4.1.5 Levels of preservation and packing (see 9.1),

4.1.6 Special markings, if required (see 9.2),

4.1.7 Method of hardness testing, if different from Rockwell “C” (see Table 1),

4.1.8 Freedom of parts from magnetic response, if required (see 1.3), and

4.1.9 Dimensions and tolerances.

## 5. Materials and Manufacture

5.1 *Materials*—The raw materials shall be a mixture of loose metal powders consisting mainly of tungsten and a

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.04 on Molybdenum and Tungsten.

Current edition approved Nov. 1, 2007. Published November 2007. Originally approved in 1987. Last previous edition approved in 1999 as B 777 - 99.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

<sup>3</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.

**TABLE 1 Composition, Density and Hardness Properties**

Class	Nominal Tungsten, weight %	Density, g/cc	Hardness <sup>A,B</sup> Rockwell "C," max
1	90	16.85–17.25	32
2	92.5	17.15–17.85	33
3	95	17.75–18.35	34
4	97	18.25–18.85	35

<sup>A</sup> When specified by the purchaser, other hardness testing methods may be employed.

<sup>B</sup> For mechanically worked or aged material, the hardness can be as high as R<sub>c</sub>46.

**TABLE 2 Mechanical Properties, Minimum Values**

Class	Ultimate Tensile Strength		Yield Strength at 0.2 % Off-set		Elongation, <sup>A</sup> %
	ksi	MPa	ksi	MPa	
1	110 <sup>B</sup>	758	75	517	5 <sup>B</sup>
2	110 <sup>B</sup>	758	75	517	5 <sup>B</sup>
3	105 <sup>B</sup>	724	75	517	3 <sup>B</sup>
4	100	689	75	517	2

<sup>A</sup> Determine with an extensometer accurate to 0.5 % elongation or less.

<sup>B</sup> Nonmagnetic composition to Classes 1, 2 and 3 shall be 94 ksi (648 MPa) minimum ultimate tensile strength. Minimum elongation shall be 2 % on Classes 1 and 2 and 1 % on Class 3.

metallic powder binder such as copper, nickel or iron, which, by sintering, will produce materials meeting the requirements of this specification.

## 6. Chemical Composition

6.1 The specified class shall have the nominal tungsten content in **Table 1**.

## 7. Physical and Mechanical Properties

7.1 *Composition, Physical and Mechanical Properties*—The sintered material shall have properties conforming to **Table 1** and **Table 2** as determined on standard sintered test bars (see Test Methods **E 8**).

7.2 *Microstructure*—The microstructure of each sample shall be a uniform distribution of tungsten particles in a binder metal matrix when viewed at a magnification of 200 times. The location may be specified (see **8.4.5**).

7.3 *Machinability*—When specified (see **4.1**), the machinability of the basic parts or of a suitable test specimen shall be such that it shall pass the test specified in **8.4.6**.

7.4 *Identification*—Each lot and associated test bars shall be clearly marked with a lot serial number (see **8.3.1**).

## 8. Quality Assurance Provisions

8.1 *Responsibility for Inspection*—Unless otherwise specified in the contract or purchase order, the manufacturer is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the manufacturer may use his own facilities for the performance of the inspection or any other facility that is acceptable to the purchaser.

8.2 *Responsibility for Compliance*—All parts must meet all the requirements agreed upon by purchaser and manufacturer from Sections **4**, **6** and **7**. The inspections set forth in this

specification shall become a part of the manufacturer's overall inspection system or quality program.

### 8.3 Quality Conformance Inspection:

8.3.1 *Inspection Lot*—An inspection lot shall consist of a uniform blend from one batch of powder, and submitted for inspection at one time. If a shipment is made from more than one lot, the purchaser may choose to consider that shipment as a single inspection lot or may choose to separate the shipment into several inspection lots for acceptance purposes.

8.3.2 *Sampling*—Unless otherwise specified, a minimum of two sintered test bars and one chemical analysis sample shall be made from each powder lot.

8.3.3 *Hardness Tests*—Each test bar shall be tested for conformance with the hardness requirements of **Table 1** (see **8.4.1**).

8.3.4 *Density*—Each test bar shall be tested for conformance with the density requirements of **Table 1** (see **8.4.2**).

8.3.5 *Tension Tests*—Each test bar shall be tested for conformance with **Table 2** (see **8.4.3**).

8.3.6 *Chemical Composition*—If specified in the purchase order, a chemical analysis sample from each lot shall be tested for the tungsten content in conformance with **Table 1** (see **8.4.4**).

8.3.7 *Examination of Microstructure*—This test shall be accomplished on one of the test bars (see **8.4.5**).

### 8.4 Methods for Test and Examinations:

8.4.1 *Hardness*—Samples shall be tested in accordance with Test Methods **E 18**.

8.4.2 *Density*—The equal water displacement method performed in accordance with Test Method **B 311** shall be used.

8.4.3 *Mechanical Properties*—Samples shall be tested in accordance with Test Methods **E 8**.

8.4.4 *Chemical Analysis*—Analysis of the lot or lots in question shall be made by Method 111 or 112 of **Fed. Std. No. 151** for conformance with **8.3.6**. In case of dispute, chemical analysis by Method 111 shall be the basis for acceptance.

8.4.5 *Microstructure*—A test bar shall be sectioned and a specimen shall be prepared for examination in accordance with Guide **E 3**. The specimen may be etched (see Practice **E 407**), and shall be examined at a magnification of 200 times for conformance with **7.2**.

8.4.6 *Machinability*—If specified by the procuring document, this test shall be made on a representative sample. Holes, 0.1695 in. in diameter and a minimum of 0.343 in. deep shall be drilled and tapped with a No. 10-32 high-speed steel tap to a minimum full thread of 0.312 in. deep. The tap shall be of high speed steel, conforming to Specification **A 600**, Type M1, heat treated to a hardness of 62-63 HRC. Machinability will be considered acceptable in each class if each of the number of holes indicated in **Table 3** is satisfactorily threaded to a minimum 60 % without destruction of the tap.

**TABLE 3 Machinability Requirements**

Class	Number of Holes
1	8
2	6
3	4
4	2

8.5 *Rejection*—Unless otherwise stated in the purchase order, failure to conform to any of the requirements of this specification shall be cause for rejection of the lot.

## 9. Packaging and Package Marking

9.1 *Preservation, Packaging, and Packing*—The material shall be prepared for delivery in accordance with the producer's commercial practice or Practice **D 3951** as specified in such a manner as to ensure acceptance for safe delivery by common or other carriers to the point of delivery.

9.2 *Marking*—If specified in the purchase order, each individual item and test bar shall be clearly identified with a lot serial number. Where parts are too small to be individually identified, they may be grouped for this purpose.

## 10. Keywords

10.1 high-density metal; tungsten

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*